

25 labeled peaks in the IR spectrum of poly(2-vinylpyridine):

Wavenumber (cm⁻¹)	Transmittance (%T)
3071.53	66.71
2947.88	68.24
2828.05	60.86
2667.87	61.98
2604.93	64.37
2089.90	83.88
1971.26	85.07
1915.70	82.75
1790.91	88.33
1618.63	62.80
1601.27	47.29
1582.83	48.78
1543.12	37.68
1496.58	71.77
1473.89	67.12
1453.12	37.68
1419.95	32.53
1323.27	29.32
1272.56	51.84
1266.59	49.08
1227.54	46.93
1173.70	48.78
1127.54	46.93
1072.56	51.84
1026.59	49.08
1000.00	68.41
973.89	67.12
907.20	43.12
844.71	25.82
703.59	8.64
665.97	11.51
601.27	47.29
544.71	25.82
431.12	43.12

Page 1